- A) a mineral oil having a cloud point of less than -8°C, a boiling range (90-20%) of less than 120°C and a difference between CFPP and PP of less than 10°C, and
 - B) one or more copolymers, wherein the copolymers comprise:
 - a) bivalent structural unit (B1), wherein (B1) is a bivalent structural unit of formula (1)

 $-CH_2-CH_2-$ (1)

and

b) one or more bivalent structural units (B2), wherein (B2) is either a bivalent structural unit of formula (2)

 $-CH_2-CR^1R^2-$ (2)

in which

R¹ is hydrogen or methyl,

R² is COOR³, OR³ or OCOR³, and

R³ is an alkyl radical having at least 4 and at most 30 carbon atoms,

or

(B2) is a bivalent structural unit of formula (2a)

$$\begin{array}{c}
-HC-CH-\\
O \longrightarrow N\\
N\\
R^{3}
\end{array}$$
(2a)

in which

R³ is an alkyl radical having at least 4 and at most 30 carbon

atoms.

25